

AU-A-44948/85

<p>86-028283/04 SANDOZ AG 03.10.84-US-657307 (+JP-125353) (16.01.86) C04b-24/6 C04b-28/2 Cement mix for mortars of improved storage ability - comprises hydraulic cement, hydroxypropyl-methyl cellulose, lignosulphonate, aggregate and water C86-012039 E(BE CH DE FR GB IT SE) N(AU BR JP KR NO)</p>	<p>A93102 SANO 20.06.84 *WO 8600-291-A</p>
<p>after mixing without affecting the other properties. The mortar has excellent adhesive properties to brick or block, adsorption of water from the mix onto the porous surface of building units is uniform, air content is stable and the strength needed to support loads placed on it is adequate.</p>	<p>The mortar is pref. prepd. by adding 0.02-0.07 wt. % (II), 0.10-0.20 wt. % sodium or calcium lignosulphonate, 0.35-0.6 wt. % sodium gluconate and 0.001-0.008 wt. % sodium alpha-olefin sulphonate to a mixt. of (I), 200-800 wt. % fine (IV) contg. up to 80 wt. % lime and 25-65 wt. % water.</p>
<p>PREFERRED EMBODIMENT</p>	<p>APPLICATION The mix is combined with a polyhydroxycarboxylic acid (V), its salt and/or a polysaccharide (VI), and an olefin or alkyl benzene sulphonate anionic surfactant to form a mortar.</p>
<p>EXAMPLE A mixt. of 0.07 wt. % hydroxypropyl methyl cellulose, 0.175 wt. % sodium lignosulphonate, 0.52 wt. % sodium gluconate and 0.008 wt. % alpha-olefin sulphonate was added to a mixt. of Type 1 Portland cement (898 g), masonry lime (100g) masonry sand (2840) with fineness modulus of 1.81 and half the required water for a water to cement ratio of 0.59.</p>	<p>PREPARATION OF MORTAR A mixt. of (I), (IV) and water is mixed with a mixt. of the other components.</p>
<p>The mortar had 24.00 vol. % air, 125% flow, cone penetration of 68, pliable consistency after 48 h. from mixing and</p>	<p>USES/ADVANTAGES The mortar is used in construction or for cementing brick, cement block, stucco or ceramic tiles. It has good storage ability and in partic. hydration of the mortar is retarded during mixing, transport and storage for up to 72 h.</p>
<p>WO8600291-A</p>	

AU-A-44948/85

good scratch resistance, workability, cohesiveness and adhesion to brick and block. (36pp 1616KJPDwgNo0/0).
(E) ISR: - GB2114985; FR1502387; FR1543999; FR2154035;
FR2085402; FR2114734; GB2040907; GB2083015.

WO 860291-A

BEST AVAILABLE COPY